

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
29 July 2004 (29.07.2004)

PCT

(10) International Publication Number
WO 2004/063108 A1

(51) International Patent Classification⁷: C03C 4/00, 3/078

Débora [BR/BR]; Rua Adriano Kormann, 409, Bela Vista,
89110-000 Gaspar-SC (BR).

(21) International Application Number:

PCT/BR2003/000199

(74) Agent: MOMSEN, LEONARDOS & CIA.; Mr. Gus-
tavo José F. Barbosa, Rua Teófilo Otoni 63, 10th floor,
20090-080 Rio de Janeiro RJ (BR).

(22) International Filing Date:

19 December 2003 (19.12.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

PI0300042-7

14 January 2003 (14.01.2003) BR

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BW, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE,
GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR,
KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK,
MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT,
RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR,
TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(71) Applicant (*for all designated States except US*): COM-
PANHA BRASILEIRA DE METALURGIA E MIN-
ERAÇÃO [BR/BR]; Rua Pequetita, 111, Vila Olímpia,
04552-902 São Paulo-SP (BR).

(84) Designated States (*regional*): ARIPO patent (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): PEREIRA, An-
tônio, Telhado [PT/BR]; Rua Esmeralda, 73, Vila
Andréia, 38182-190 Araxá-MG (BR). MENEZES,
Andreia, Duarte [BR/BR]; Rua Colibris 62, Área 1,
38182-192 Araxá-MG (BR). STRAUSS, Frederico,
Werner [BR/BR]; Rua Arnold Beck, 300, Itoupava
Central, 89062-270 Blumenau-SC (BR). DA SILVA,

Published:

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: GLASS COMPOSITIONS FOR THE PRODUCTION OF LEAD-FREE CRYSTALS

(57) Abstract: The invention refers to glass compositions for the production of lead-free crystals, having a density greater than 2.4g/cm³, a refractory index of at least 1.51 and high resistance to chemical attack, characterized by comprising, by weight: from about 50% to about 75% of SiO₂; from about 0,1% to about 1% of As₂O₃; from about 5% to about 15% of K₂O; from about 2% to about 6% of Na₂O; from about 3% to about 12% of CaO; from about 0,1% to about 5% of BaO; from about 0,1% to about 10% of Nb₂O₅; and, up to 5% of other elements.

WO 2004/063108 A1

"GLASS COMPOSITIONS FOR THE PRODUCTION OF LEAD-FREE CRYSTALS"

5 Technical Field

Present invention refers to glass compositions for the production of lead-free crystals, having a density greater than 2.4 g/cm³ and a refractory index of at least 1.51, that may be used for the production of fine tableware and decorative objects with similar characteristics (sound, brilliance, transparency, malleability) to those found in objects made with a formulation of 24% PbO.

The necessity to produce new types of glass with the same characteristics of crystal with 24% of PbO stems from the fact that lead, as well as its components; presents certain toxicity when in direct contact with humans. For this reason, whenever it is technically possible, one should opt for less toxic alternative products.

The proposal of the present invention is the substitution of lead with niobium in glass compositions.

20 Background of the Invention

Due to lead's toxicity, this invention has come with the proposal of removing it from the basic formulation of crystal, replacing it with niobium, which is totally inert, presenting no risk to those who handle it or come into direct contact with it.

25 Due to this, research has been carried out in the search for materials that can substitute lead in fine tableware crystal. It is known that,

even if in small amounts, lead can separate from the glass.

United States patent 6,333,288 on optical glass, discloses that Nb_2O_5 and La_2O_3 increase the refractory index. Besides this, both components
5 can increase the transmission of the glass.

United States patent 4,224,074 concerning raw materials for glass, discloses that the use of ZrO_2 increases the refractory index and offers exceptional chemical durability. It also discloses that TiO_2 and HfO can be
10 added to increase the refractory index.

European patent application EP 0594422A, referring to the composition of glass, discloses that when the percentage of TiO_2 is less than 5%, the target values for refractory and dispersion indexes cannot be
15 obtained. On the other hand, when the percentage of TiO_2 exceeds 8%, the tendency for the appearance of yellow coloring increases significantly; this being an undesired quality for crystal where transparency is very important.

United States patent 6,184,166 discloses compositions for
20 lead-free glass, where the PbO is substituted with ZnO . This substitution, along with the alkaline oxide control, offers the desired characteristics of viscosity, previously achieved with the use of lead oxide. Nowadays, glass, containing zinc oxide, has better resistance than the ones containing lead oxide, besides offering enhanced durability in reference to chemical attack.
25 Nevertheless, it is known that ZnO introduced into glass mixture can contain relatively high levels of CdO , a highly toxic substance, even in low concentrations.

Summary of the Invention

Thus, the purpose of the present invention is to provide glass compositions for the production of lead-free crystals, having a density greater than 2.4g/cm^3 , a refractory index of at least 1.51 and high resistance to chemical attack, characterized by comprising, by weight: from about 50% to about 75% of SiO_2 ; from about 0,1% to about 1% of As_2O_3 ; from about 5% to about 15% of K_2O ; from about 2% to about 6% of Na_2O ; from about 3% to about 12% of CaO ; from about 0,1% to about 5% of BaO ; from about 0,1% to about 10% of Nb_2O_5 ; and, up to 5% of other elements.

In a particular embodiment, the composition comprises, by weight: from about 60% to about 75% of SiO_2 ; from about 0.1% to about 1% of As_2O_3 ; from about 6% to about 15% of K_2O ; from about 2% to about 6% of Na_2O ; from about 3% to about 10% of CaO ; from about 0.1% to about 5% of BaO ; from about 0.1% to about 10% of Nb_2O_5 ; and, up to 5% of other elements.

In the composition:

Silica (SiO_2) is responsible for the basic network formation of glass;

The percentages of Na_2O and K_2O work as modifiers of the network and act as fluxes, facilitating the crystal casting. Adverse effects are that excessive increases of these components increase the thermal expansion coefficient which is usually undesirable and diminishes the chemical durability.

CaO is the most important earthy alkaline for the formation of glass.

BaO and CaO can be used to assure the high density and the

high refractory index.

Nb_2O_5 is used to increase the refractory index as well as the chemical and physical resistance of the crystal.

Among the additives which facilitate refining, As_2O_3 can be used up to the amount of 1%. The crystal can even contain discoloration agents such CoO , NiO , and Nd_2O_3 .

The measurement of the refractory index was carried out with the help of a Abbe Refractometer from Atago. For the hardness measurement a Future Tech Corporation FM micro-hardness meter was used, with a semi-automatic reading device. The identification load was 50g. The analyses were carried out on polished glass surfaces and 7 measurements were made for each sample. The refractory index and micro-hardness tests were performed in the Vitreous Materials Laboratory (LaMaV) at the Federal University of São Carlos.

The thermal expansion coefficient measurement was done in accordance with the Annex K of Brazilian Norm NBR 13818:1997. This analysis was carried out at the Material Characterization and Development Center (CCDM).

The thermal expansion coefficient determination test revealed the following data:

The Annealing Point (AP): The annealing point corresponds to the maximum temperature in the annealing range in which the internal force of the glass will be substantially eliminated.

The Softening Point (SP): The softening point is the temperature at which the glass becomes deformed by its own weight.

The Glass Transition Temperature (T_g): The glass transition temperature is the temperature range at which the glass is gradually transformed from its solid state to its molding state. The transformation temperature can be determined through the thermal expansion curve.

5 The Thermal Expansion Coefficient (α): A mass expands when it is heated. Thermal expansion is the change relative to a given dimension when a mass is heated.

The chemical durability was tested by weighing the mass after being treated in pH 1 and neutral solutions, at different times, at a temperature
10 of 50°C.

Detailed Description of the Invention

In order to overcome the inconveniences of lead-free crystals discussed earlier, a reformulation of the mixture is proposed (% in weight of oxide)
15 for the manufacturing of lead-free glass objects described in tables 1 and 2 below:

Table 1: Chemical Properties of the Niobium Crystal

Chemical Properties		
Elements	Test 1	Test 2
%SiO ₂	72	74
%As ₂ O ₃	0,3	0,3
%K ₂ O	10,6	11
%Na ₂ O	5,2	5,4
%CaO	5,1	5,3
%BaO	2	2
%Nb ₂ O ₅	4,6	1

Table 2: Physical Properties of the Niobium Crystal

Physical Properties		
Property	Test 1	Test 2
(S.P.) °C	592	577
Tg °C	521	516
(α)x10 ⁻⁷ /°C	85,3	99,9
Density (g/cm ³)	2,52	2,7
nd	1,52	1,51
Hardness (Hv) kgf/mm ²	521*/-8	502 +/- 5

5 The chemical resistance of the samples (see Table 3) was evaluated by analyzing the weight loss after immersion in a neutral solution for periods up to 105 hours and in a pH 1 solution up to 57 hours. The results are shown in Figures 1 and 2 and it may be observed that the samples that contain Nb₂O₅ suffered less chemical attack.

10

Table 3: Percentage of Nb₂O₅ and PbO in the Tests Analyzed

Sample	%Nb ₂ O ₅	PbO
4%PbO	0	4
24%PbO	0	24
4%Nb ₂ O ₅	4	0
1%Nb ₂ O ₅	1	0

CLAIMS

1. Glass compositions for the production of lead-free crystals, having a density greater than 2.4g/cm^3 , a refractory index of at least 1.51 and high resistance to chemical attack, characterized by comprising, by weight: from about 50% to about 75% of SiO_2 ; from about 0,1% to about 1% of As_2O_3 ; from about 5% to about 15% of K_2O ; from about 2% to about 6% of Na_2O ; from about 3% to about 12% of CaO ; from about 0,1% to about 5% of BaO ; from about 0,1% to about 10% of Nb_2O_5 ; and, up to 5% of other elements.

2. The glass compositions of claim 1, characterized by comprising, by weight: from about 60% to about 75% of SiO_2 ; from about 0.1% to about 1% of As_2O_3 ; from about 6% to about 15% of K_2O ; from about 2% to about 6% of Na_2O ; from about 3% to about 10% of CaO ; from about 0.1% to about 5% of BaO ; from about 0.1% to about 10% of Nb_2O_5 ; and, up to 5% of other elements.

Corrosion test pH = 1




FIG. 1

Corrosion test pH = 7




FIG. 2